

BESS Cell 314 Ah

Prismatic LFP cell optimised for use in stationary BESS



Prismatic LFP cell with very high cyclic lifetime and improved safety characteristics.

Specially optimised for use in stationary battery storage systems with the highest requirements on safety, reliability and performance. Suitable e.g. for industrial, utility, and grid serving applications.

- Product certifications:IEC 62619, UL 1973, UL 9540A, UN 38.3
- Company certifications: ISO 9001, ISO 14001, ISO 45001
- Environmental Compliance: ROHS, REACH

High safety

- HiTHIUM-developed prismatic LFP cell with high thermal stability
- Passes crush and nail penetration test
- Ultra wide operating temperature range

Low LCOS (Levelised Cost of Storage)

■ Long life cycle > 11,000 cycles at 0.5P/0.5P 70% SOH due to advanced materials and process technologies

Flexible and versatile use

Preliminary

BESS Cell 314 Ah

Prismatic LFP cell optimised for use in stationary BESS



314 Ah ^{1, 2}
1,004.8 Wh ^{1,2}
LiFePo4 (LFP)
> 11,000 ^{1,2,3}
> 175 Wh/kg
> 385 Wh/I
LFP71173207

ELECTRICAL	
Nominal Voltage	3.2 V ^{1,2}
Operating Voltage	T > 0°C 2.50 3.65 V
	T ≤ 0°C 2.00 3.65 V
AC Resistance (1 kHz)	0.20 mΩ +/- 0,05 ⁴
Max. self discharge rate	3% / month ^{2,4}
Nominal SOC at delivery	27 % ²
Max. continuous charge rate	1 P
Max. continuous discharge rate	1 P

ELECTRICAL	
Nominal Voltage	3.2 V ^{1, 2}
Operating Voltage	T > 0°C 2.50 3.65 V
	T ≤ 0°C 2.00 3.65 V
AC Resistance (1 kHz)	0.20 mΩ +/- 0,05 ⁴
Max. self discharge rate	3% / month ^{2,4}
Nominal SOC at delivery	27 % ²
Max. continuous charge rate	1 P
Max. continuous discharge rate	1 P

PRODUCT CERTIFICATIO	NS
Certificates and Reports	L II

ENVIRONMENTAL	
Compliance	ROHS, REACH
	Cobalt free

COMPANY CERTIFICATIONS

Dimensions (L x W x H)

TEMPERATURE RANGE

Storing (recommended)

Type

Weight Volume

Charging **Discharging**

ISO 9001, ISO 14001, ISO 45001

174.7 x 71.70 x 207.11 mm

prismatic

2.59 I

5.65 kg +/- 0.2

0°C ... 60°C ⁵

IEC 62619

-30°C ... 60°C ⁵

-20°C ... 35°C (+5°C ... 35°C) 5

UN 38.3, UL 9540A, UL 1973,

HiTHIUM Energy Storage Technology USA Inc.

Address: 4046 Clipper Ct, Fremont, CA 94538, United States Email: hithium@hithium.com

Xiamen HiTHIUM Energy Storage Technology Co., Ltd.

Address: HiTHIUM Industrial Park, Tongxiang High-Tech Zone, Xiamen, Fujian, China | Email: hithium@hithium.com





¹ 0.5 P / 0.5 P

² 25 °C +/- 2.0

³ 70 % SoH

^{4 27 %} SOC

⁵ Ambient temperature